



-2-

7518935

Background of the Invention1. Field of the Invention

This invention relates to a process for reclaiming useful pulp fibers from wood-containing or wood-free wastepaper by a biological method in the de-inking process.

2. Description of the Background

De-inking of pulp fibers is essentially a laundering or cleaning process in which the ink is considered to be the dirt.

Chemicals, along with heat and mechanical energy, are used to dislodge the ink particles from fibers and to disperse them in the aqueous medium. The ink particles are then separated from the pulp fibers, either by washing or flotation or by using a modern hybrid process that combines washing and flotation.

The chemicals used for the conventional de-inking process are surfactants which function as detergents to remove ink from the fiber, as dispersants to keep the ink particles dispersed and prevent redeposition on the fibers, and foaming agents in the froth flotation of ink particles.

A typical surfactant is a long chain molecule with a hydrophobic part on one end and a hydrophilic part on the other end. The hydrophobic part may consist of fatty acid, fatty alcohol, alkylphenols or other oil-soluble surfactants.

The hydrophilic part in the de-inking surfactant usually consists of anionic molecules, such as carboxylic acid salts or sulfonic acid salts and nonionic molecules, such as polyoxyethylenated chains.

The typical surfactants commonly used in the washing and froth flotation de-inking processes are: sodium and potassium salts of straight-chain fatty acids (soaps), linear alkylbenzenesulfonates (LAS), long-chain fatty alcohols, polyoxyethoxylated alkylphenols, alkylphenol-ethoxylates, and polyoxyethoxylated straight-chain alcohols.

A major disadvantage of using these surfactants in the de-inking process is excess foaming in the subsequent pulp stock flow and papermaking process lines. Moreover, some of

the above surfactants are resistant to biodegradation in the effluent treatment stages causing a serious environmental problem.

In the froth flotation de-inking process, a collector
5 is added to agglomerate ink into large particles and attach them to the air bubbles. Collectors are required for effective flotation and are usually anionic long-chain fatty acid soaps. Fatty acid collectors are precipitated with
10 calcium ions to form larger, insoluble ink particles and collector particles. With injection of air in the flotation cells, the agglomerated ink particles adhere to the bubbles, rise to the surface and are skimmed off from the system.

Major disadvantages of the flotation method using the fatty acid collector are a pitch deposition and calcium
15 scaling problems in the subsequent stock lines and papermaking process equipment. Besides surfactants, other chemicals employed are caustic soda, sodium silicate, metal ion chelating agents and hydrogen peroxide.

The hydrogen peroxide bleaching agent has to be added
20 in order to prevent pulp yellowing caused by the addition of caustic soda and to improve the brightness of pulp fibers.

With advances in modern printing and photocopying technology, conventional de-inking with the aid of surfactants encounters serious problems because the
25 wastepaper is printed with the use of heavily coated, highly polymerized or non-impact inks, such as ultraviolet, heat-set, Xerox, laser and ink jet. These inks usually contain cured polymer resins which bind ink particles so strongly on the fiber surface that it is impossible to dislodge the inks
30 completely during the wastepaper defiberizing (pulp) stage with the conventional de-inking chemicals. Excess heat and mechanical energy are also required along with the ineffective conventional chemicals.

Furthermore, in the conventional flotation de-inking
35 process for newsprint wastepaper, a major technical problem has to do with the fact that fine ink particles are embedded in the fiber bundles and between fibrils which are almost impossible to be removed from the fibers by a washing and/or

THIS PAGE BLANK (USPTO)

-4-

flotation process.

Summary of the Invention

This invention provides a new and much improved de-inking method which is effective for newsprint as well as wood-free printed wastepaper, such as whiteledger, laser
5 printed, xerographic copypaper and computer printout wastepaper.

The de-inking method of the present invention is to remove ink particles by the use of the biological activity of enzymes on the cellulose fiber surface and the dispersing
10 function of enzyme protein on ink particles.

In contrast to the conventional method, no alkali or de-inking surfactants are required, although some surfactants can be used along with the enzyme to enhance the de-inking efficiency. In the froth flotation process, the
15 fatty acid collectors are not required. Since caustic soda is not used in the newsprint de-inking, a hydrogen peroxide bleaching agent is also not required for preventing yellowing.

The elimination of the fatty acid collector in this
20 biological de-inking process will solve the persistent pitch and scale deposition problem associated with the conventional flotation process using the fatty acid type soap and calcium salts and silicates.

25

30

35

Description of the Preferred Embodiment

The wastepaper, such as old newsprint, is disintegrated in a conventional pulper (consistency 4-7%) or in a high consistency pulper, (consistency 12-15%), at a water temperature ranging from room temperature ^(20°C - 25°C) up to 60°C. The addition level of enzyme is 0.005% to 5.0% by weight based on dry weight of wastepaper. The pH of the stock slurry is adjusted in the range of 3.0 to 8.0. As compared to the conventional pulping process using caustic and surfactants, the pulping in the presence of enzyme can be completed in a relatively short period and ink particles are completely separated from the fiber surface and dispersed well. The dispersed inks are removed out of the pulp fibers by using the conventional washing process equipment, such as vibrating screen and drum washers without the aid of detergent surfactants in single and multi-stages. The ink particles dispersed with the action of enzyme protein can be also selectively removed out of the diluted pulp slurry with conventional flotation equipment in which air is injected or drawn into the pulp to provide bubbles to pick up the particles. No fatty acid collector is required in the case of waste newsprint. A small amount of fatty acid collector may be added to enhance the ink removal efficiency in the case of laser-printed wastepaper.

Among enzymes which can be used in the method are the carbohydrases and particular enzymes, such as cellulase, hemicellulase, pectinase and mixtures thereof.

This biological de-inking process lowers pulping energy requirements to a large extent (almost 50% reduction) since the addition of enzyme results in a substantial reduction in pulping time as compared to the pulping in the absence of enzyme. The observed faster and easier pulping in the presence of enzyme may be attributed to the unique biological activity of the enzyme which is effective to debond the fiber bonding and dislodge the inks bonded on the fiber surface as well as within the fiber bundles or between the fibrils. A partial enzymatic hydrolysis of cellulose within the micro structure of the fiber surface may occur

during the pulping stage. Because of this biological activity of the enzyme, the fine ink particles embedded within fiber bundles, fibrils and fines which have been impossible to be taken out by the conventional de-inking chemicals in the case of old newsprint de-inking are removed.

According to this biological de-inking method of old newsprint, the addition of hydrogen peroxide to prevent fiber yellowing is not required. This results in a substantial reduction of de-inking chemical cost as compared to the conventional de-inking process using caustic soda, hydrogen peroxide, chelating agents and sodium silicates.

It should be pointed out that the physical strength properties of the resulting pulp fiber prepared by this invented method are found to be higher than those of the corresponding pulp prepared by the conventional method in addition to the much higher resulting pulp brightness. The enzyme addition does not appear to degrade the fiber strength, but rather improves the fiber strength for reasons not presently known.

To more fully illustrate the present invention, the following non-limiting examples are presented.

Example 1

25 De-inking of Old Newsprint with a Cellulolytic Enzyme.

A sample of old newsprint wastepaper was added to the pulper which was filled with 40°C water at a consistency of 4% and cellulase (enzyme) was dissolved at the dosage level of 0.1% based on oven dry weight of wastepaper. The wastepaper was soaked for 10 minutes and then disintegrated for 5 minutes. After a complete disintegration of wastepaper, one half of the pulp slurry was diluted to 1% consistency.

The diluted pulp slurry was moved to the air flotation cell and then the dispersed ink particles were removed out of the pulp slurry by skimming off the ink particles froth out of the cell while injecting air through a porous plate. The flotation time for the complete removal of the

ink froth was one minute.

The other half of the pulp slurry was washed on a laboratory vibrating screen to remove the dispersed ink particles.

5 The resulting recycled pulp fibers obtained by the flotation and the washing step were evaluated for pulp brightness and mechanical strength properties. To compare this enzyme-treated de-inked pulp to the conventional de-inked pulp, the same sample of wastepaper was treated in the
10 pulper with addition of 1.0% NaOH, 0.3% H_2O_2 , 3% sodium silicate solution (water glass) and 0.8% of SERFAX MT-90 (fatty acid soap) and 0.2% IGEPAL-660 (biodegradable nonionic surfactant marketed by GAF Corporation) based on
15 oven dry weight of wastepaper. The pulping time was 10 minutes for a complete disintegration. After diluting to 1% consistency, the dispersed ink particles were removed by the flotation method with the laboratory flotation cell as described above.

20 As shown in Table 1, the brightness of the pulp de-inked with enzyme was much higher than that of the pulp de-inked with the conventional chemicals and the mechanical strength of the enzyme-de-inked pulp was also superior to the pulp de-inked with the fatty acid collector and the dispersant (IGEPAL-660). Microscopic observation revealed
25 that the pulp prepared by the present invention contained more long fiber fractions, has smoother fiber surface and looks less mechanically damaged.

30

35

Table 1. Comparison of properties of recycled pulp by the method of the present invention and the conventional method.

	brightness (%)		tensile index (N.m/g)		tear index (mN.m/g)	
	KONP	AONP	KONP	AONP	KONP	AONP
present flotation method	47.1	45.2	28.9	32.4	11.7	13.6
washing	50.3	48.6	29.3	32.9	11.8	14.1
conventional method	45.1	38.4	30.1	32.8	10.8	13.1

KONP: Korean old newspaper
AONP: American old newspaper

As can be seen from the data in Table 1, the enzyme-treated pulp gave cleaner and brighter pulp with the washing as compared to the flotation ink removal using the conventional method.

The enzyme addition also appeared to accelerate the wastepaper disintegration to a large extent. When the old newspaper was disintegrated in the conventional pulper at the 4% consistency, the addition of 0.5% enzyme reduced the pulping time from 5 minutes (no enzyme addition) to 30 seconds for a complete disintegration as shown in Table 2.

Table 2. Relation between enzyme addition and disintegration time.

enzyme (%) (cellulase)	0.5	0.1	0
disintegration time (sec)	30>	60-120	300<

Example 2

De-inking of Laser CPO (computer printout) with Cellulolytic enzyme.

It is almost impossible to achieve a complete removal of laser beam cured ink particles from the laser CPO wastepaper with the conventional de-inking chemicals, because the ink particles are so strongly adhered to the fiber surface that alkali and general de-inking surfactants used in the conventional process are not able to dislodge and disperse the ink in the pulp-water slurry.

A sample of laser-CPO wastepaper was added to water in a laboratory high consistency pulper to achieve a consistency of 12.5% and a cellulase (enzyme) was added to the water at the dosage level of 0.2% based on the dry weight of paper. At stock water temperature of 20-35°C, the pulping was carried out for 20 minutes. The completely disintegrated pulp slurry was diluted to 0.5% consistency and then the dispersed ink particles were removed out of the pulp slurry using the laboratory flotation cell in the same way described in Example 1. In this case, to increase the ink removal efficiency and selectivity, a small amount of the conventional fatty acid collector, SERFAX MT-90, 0.3% based on dry weight of wastepaper, was added prior to the air flotation step and the flotation time was 3 minutes. To compare to the enzyme de-inked pulp, the conventional de-inked pulp was prepared by the same way but the following chemicals and conditions were used:

1% NaOH on dry weight of wastepaper
0.1% IGEPAL-660 dispersant
0.8% SERFAX MT-90
pulping temperature: 50°C
pulping time: 30 minutes
calcium salt addition to the flotation cell: 200ppm
flotation time: 3 minutes

The brightness and the strength properties of the resulting pulp samples were compared in Table 3.

Table 3. Comparison of pulp properties recycled by the method of the present invention and the conventional method.

	brightness (%)	dirt amount (count/area)	tensile index (N.m/g)
enzyme + MT-90(0.3%)	79.0	450	34.3
MT-90 (0.8%) (conventional method)	80.6	4,330	26.3

Example 3

15

De-inking of waste newsprint by pectinolytic enzyme.

As per the method of Example 1, the waste newsprint containing 0.1% of pectinase was soaked for 10 minutes at 40°C and disintegrated for 5 minutes. The disintegrated pulp was diluted to a consistency of 1%. Ink particles were removed by flotation for 1 minute.

As shown in Table 4, the brightness and the tensile strength of paper sheet prepared by the method of the present invention are improved.

25

Table 4. Comparison of the method of using pectinolytic enzyme with the conventional method.

	brightness (%)	tensile index (N.m/g)
present method	44.2	33.3
MT-90 (0.8%) (conventional method)	38.4	32.8

-12-

The foregoing disclosure and description of the invention is illustrative and explanatory thereof, and various changes in the method steps may be made within the scope of the appended claims without departing from the
5 spirit of the invention.

What Is Claimed Is:

Sub
B1

1. A method of de-inking wastepaper comprising pulping waste printed paper with an enzyme capable of dislodging ink particles from the pulped paper and removing dislodged ink particles.

2. The method of Claim 1 wherein said ink particles are removed by flotation.

3. The method of Claim 1 wherein said ink particles are removed by washing.

4. The method of Claim 1 wherein said enzyme is selected from the class consisting of cellulase, hemicellulase, pectinase and other carbohydrases and mixtures thereof.

5. The method of Claim 1 wherein the amount of enzyme used is in the range of 0.005% to 5% by weight based on the dry weight of the wastepaper.

6. The method of Claim 2 wherein the amount of enzyme used is in the range of 0.005% to 5% by weight based on the dry weight of the wastepaper.

7. The method of Claim 1 including controlling the temperature of the pulping process in a range of from room temperature up to about 60°C.

8. The method of Claim 1 including controlling the pH of the pulping process in a range of from 3 to 8.

add
a2

Abstract of the Disclosure

A method of de-inking wastepaper by pulping the paper in the presence of an enzyme which dislodges the ink particles from the paper fibers and removing the dislodged
5 ink particles by a method, such as flotation or washing.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☒ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☒ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☒ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.